



MARQUINIA SERIES


(1 Surface & 9 Faces)




Coordinated Mosaics



Available Colors



NERO



GOLD



TECHNICAL SPECIFICATION

President Ceramic

SR.NO	CHARACTERISTICS	TEST METHOD	STANDARDS AS PER ISO-13006;2013 GROUP BIa	OUR GENERAL TECHNICAL STANDARDS FOR HIGH GLOSS
A DIMENSION & SURFACE QUALITY				
1	Deviation in length & width	ISO-10545-2	±0.5 %	± 0.3 %
2	Deviation in thickness	ISO-10545-2	±5.0 %	±5.0%
3	Straightness of side	ISO-10545-2	±0.5 %	± 0.5%
4	Rectangularity	ISO-10545-2	±0.6 %	± 0.35 %
5	Surface flatness	ISO-10545-2	±0.5 %	± 0.40 %
6	Surface quality	ISO-10545-2	95% OF the tiles free from visible defect	95%

B PHYSICAL PROPERTIES				
1	Water absorption	ISO-10545-3	≤ 0.5%	≤ 0.5%
2	Modulus of rupture	ISO-10545-4	> 35 N/MM ²	> 35 N/MM ²
3	Flexure breaking strength	ISO-10545-4	> 1300n	2000n
4	Moisture expansion	ISO-10545-10	0.02%	nil
5	Thermal expansion	ISO-10545-8	6x10 ⁻⁶ k ⁻¹	6.5x10 ⁻⁶ k ⁻¹
6	Thermal shock resistance	ISO-10545-9	min 10 cycle	10 cycle passed
7	Frost resistance	ISO-10545-12	no damage	no damage
8	Glossiness (Only for Polished Surface)	gloss meter	as per mfg.norms	≥90 ^o

Disclaimer : Above test results are based on the samples randomly drawn from the production lot at the time of generating report. Properties might vary depending on different surface, application, colour, size and thickness of the product. We reserve the rights to amend or delete either totally or partially, the sizes, references and other technical specifications contained in the table above.



Address :
The President Group
 At, Trajpar, 8-A, National Highway,
 Old Ghuntu Road, Morbi-363642.
 Contact : +91 9023 920 621
 Email : Export@thepresidentgroup.com

Follow Us



For more sizes log in to :
www.presidentceramic.com
www.thepresidentgroup.com



PRESIDENT
GROUP

